


Technical Bulletin

輸入元：(株)テクノセット 東京都中野区南台 4-59-8 TEL. 03-3383-2290

Product:	Syna Epoxy 510 (N,N-Diglycidyl-4-glycidyoxyaniline)
Chemical Name	N,N-Diglycidyl-4-glycidyoxyaniline
CAS Number	5026-74-4
EINECS No.	225-716-2
Formula	C ₁₅ H ₁₉ NO ₄
Mol.Wt	277.32 g/mol

Structure**Description:**

Tri-functional, low viscosity epoxy resin
Fast cure speed
Excellent mechanical performance and heat resistance
Excellent anti-solvent and anti-corrosion ability

Typical Properties:	Appearance: Yellowish liquid
	EEW 95 – 106 g/Eq.
	Viscosity, 400 – 850 cPs 25 °C (77 °F)

Storage & Stability:	NEVER store at warm places. Avoid any kind of heat source. Avoid acidic or basic substances. Avoid direct exposure to sunshine. Store in a dry location at low temperature, 4°C (40 °F) or below is strongly recommended. Warm the container gradually by letting it stand in an area at room temperature prior to use.
Effective Date:	01-Jan-2013
Supersedes:	N/A

These data are typical values and cannot be construed as specifications.

輸入元：株式会社テクノセット〒164-0014 東京都中野区南台4-59-9
TEL. 03-3383-2290 FAX. 03-4578-1866**TECHNOSET CO., LTD. TOKYO, JAPAN**